

Preparation of Biopasalgira Pellet as A Candidate Media to Reduce Hardness of Water

by Choirul Amri

Submission date: 12-Aug-2020 02:45PM (UTC+0800)

Submission ID: 1368715911

File name: Preparation_of_Biopasalgira_Pellet_as_A_Candidat_M.pdf (939.1K)

Word count: 1245

Character count: 6429

2

See discussions, stats, and author profiles for this publication at: <https://www.researchgate.net/publication/330796476>

Preparation of Biopasalgira Pellet as A Candidat Media to Reduce Hardness of Water

Conference Paper · January 2018

DOI: 10.4108/eai.24-10-2018.2280504

CITATIONS

0

READS

16

1 author:



Choirul Amri

Poltekkes Kemenkes Yogyakarta, Indonesia

19 PUBLICATIONS 18 CITATIONS

[SEE PROFILE](#)

Some of the authors of this publication are also working on these related projects:



Nanomaterials, design and applications [View project](#)

Preparation of Biopasalgira Pellet as A Candidate Media to Reduce Hardness of Water

Choirul Amri¹
{choirul.amri@poltekkesjogja.ac.id¹}

8

Department of Environmental Health, Poltekkes Kemenkes Yogyakarta, Jl. Tatabumi no 3
Banyuraden, Gamping Sleman, Yogyakarta, Indonesia 55293¹

Abstract. Various efforts to reduce hardness continue to be carried out in the framework of providing water that meets the requirements. At the same time, it is necessary to strive for the development of Indonesia's natural resource potential which is possible to be a media candidate to reduce hardness, one of which is seaweed. Seaweed contains alginate polymer with carboxylic groups which in acidic conditions are insoluble in water and can bind calcium (Ca) ions, so it is expected to be used as a media candidate to reduce hardness. In this study, the preparation of alginic acid was related to the ease of use and stability in water. The results showed that as a media candidate to reduce hardness, alginic acid could be prepared in the form of pellets. This alginic acid pellet has good stability at pH less than 7.

Keywords: alginic acid, pellet, stability, hardness.

1 Introduction

Various community complaints related to water hardness problems continue to emerge, ranging from physical water, crusting, to indirectly related to the impact on their health. Many efforts have been made to reduce water hardness, including heating, precipitation, sedimentation, and most commonly to reduce hardness by ion exchange. As an ion exchange medium zeolites and resins are often used.




Fig. 1. Structure of alginates with block types of guluronic and manuronic bonds[1][2].

6

ICCSET 2018, October 25-26, Kudus, Indonesia
Copyright © 2018 EAI
DOI 10.4108/eai.24-10-2018.2280504

Indonesia is rich in natural ingredients in addition to zeolites which need to be studied in relation to reducing water hardness. One of them is seaweed. Seaweed contains an alginate that can be separated from the parent structure. This alginate is known as a water-soluble polysaccharide consisting of β -D-Manuronates and α -L-Guluronates which are linked to bonds (1-4)[3]. The alginate structure is presented in Figure 1.

In each alginate monomer there is a carboxylic group. Under acidic conditions, this group causes the formation of guluronic acid and or manuronic acid. This will cause intramolecular hydrogen bonds[3], and as a result form alginic acid formations (biopasalgira = seaweed alginate acid biopolymer) which are not water soluble [4]. Hydrogen ions which are bound to carboxylic groups from this alginate can be replaced by hardness-causing metal ions, especially calcium (Ca), which is expected to reduce water hardness.

As a candidate for media to reduce hardness, this alginic acid polymer needs to be designed regarding its ease of use and stability. Therefore, in this study biopasalgira was designed in the form of pellets. Alginate polymers under acidic conditions are not soluble in water, so it is necessary to determine the stability of biopasalgira in water at varying water pH. For this reason, this study will be reviewed.

2 Experimental

2.1 Preparation of Biopasalgira Pellets

Sodium alginate powder is made in the form of pellets with a pelletizer, then made alginic acid through soaking in 1 M HCl solution for 24 hours, and dried.

2.2 Determination of The Stability of Biopasalgira Pellets

Biopasalgira pellet stability was tested according to Amri et al (2015), namely by weighing the weight of the pellets (W1), then the pellets were soaked in water with a variety of pH (pH 3,4,5, ... 10) for 4 hours. The pellets were dried in an oven at 40 ° C for 24 hours, desiccated for 1 hour, then weighed (W2). Polymer stability (SP) at each pH was calculated using equation (1) [2].

$$SP = \left[1 - \frac{W1-W2}{W1} \right] \times 100 \quad (1)$$

3 Result and Discussion

Indonesian natural materials polymers continue to be used. In this paper, alginate seaweed polymer is developed as a media candidate to reduce hardness. Related to its ease of use, seaweed alginate polymer is made in the form of pellets as alginate acid (biopasalgira). To make this bioasalgira pellet, alginate which is still in the form of sodium alginate plus water to form a solid paste, then formed into pellets using a pellet printer. The printed pellets are soaked in 1 M HCl solution for 24 hours until the pellets form a hard mass, then dried in the sun to dry. Alginate acid pellet formation was investigated using FTIR at 4000-500 cm^{-1} wave number. In **Figure 2** presented the infrared (IR) spectra of sodium alginate and biopasalgira pellets.




Fig. 2. FTIR spectra of (a) sodium alginate (a), and (b) biopasalgira pellets.

The carboxylic group in sodium alginate appeared at 1620 cm^{-1} , while in biopasalgira pellets at 1736 cm^{-1} . This peak shift of the carboxylic group indicates that the biopasalgira pellet has been formed. Taha et.al (2005) reported indications of alginate acid formation at a peak of 1752 cm^{-1} [5]. Alginate in the form of alginic acid is reported to not dissolve in water. However, the use of biopasalgira pellets as a candidate of media to reduce hardness needs to be determined its stability.

The stability of biopasalgira pellets is determined in order to provide information on the pH of the water, how many alginate acid pellets can be used. In Figure 3 presented the stability of alginate acid pellets at various pH of water. Based on the stability test data, this alginic acid pellet has good stability at water pH <7, so that the biopasalgira pellets can be used as a candidate of media to reduce water hardness which is less than 7 of pH or arranged in advance so that the water pH is less from 7.




Fig. 3. Stability of biopasalgira pellets at various of pH.

4 Conclusion

The use of seaweed alginate as a media candidate to reduce water hardness can be made in the form of biopasalgira pellets. Biopasalgira pellets have good stability at pH less than 7.

References

- [1] S. Kanakasabai, "Alginate Strings and Their Applications in Spinal Cord Regeneration," Drexel University College of Medicine, Drexel, 2005.
- [2] C. Amri, D. Mudasar, Siswanta, and R. Roto, "Characterization of butanediol-alginate ester as candidate of hemodialysis membrane," *Indones. J. Chem.*, vol. 2, 2015.
- [3] A. W. Chan, "Controlled Synthesis of Stimuli-Responsive Network Alginate," Queen's University Kingston, Ontario, Canada, 2009.
- [4] M. Davidovich and H. Bianco, "A Quantitative Analysis of Alginate Swelling," *Carbohydr Polym*, vol. 19, pp. 1020–1027, 2010.
- [5] M. O. Taha, K. M. Aiedeh, Y. Al-Hiari, and H. Al-Khatib, "Synthesis of zinc-crosslinked thiolated alginic acid beads and their in vitro evaluation as potential enteric delivery system with folic acid as model drug," *Pharmazie*, vol. 60, no. 10, pp. 736–742, 2005.

Preparation of Biopasalgira Pellet as A Candidate Media to Reduce Hardness of Water

ORIGINALITY REPORT

15%

SIMILARITY INDEX

10%

INTERNET SOURCES

13%

PUBLICATIONS

11%

STUDENT PAPERS

PRIMARY SOURCES

- 1 M. Saquib Hasnain, Amit Kumar Nayak, Mukul Singh, Mohammad Tabish, Mohammed Tahir Ansari, Tahseen Jahan Ara. "Alginate-based bipolymeric-nanobioceramic composite matrices for sustained drug release", International Journal of Biological Macromolecules, 2016
Publication 3%
- 2 Submitted to American Museum of Natural History
Student Paper 3%
- 3 Ramy Mohamed Ghazy, Abdallah Almaghraby, Ramy Shaaban, Ahmed Kamal et al. "Effectiveness and Safety of Chloroquine or Hydroxychloroquine as a mono-therapy or in combination with Azithromycin in the treatment of COVID-19 patients: Systematic Review and Meta-Analysis", Cold Spring Harbor Laboratory, 2020
Publication 2%

Submitted to Heriot-Watt University

4	Student Paper	1%
5	Jiwei Li, Jinmei He. "Alginate-based Films and Membranes: Preparation, Characterization and Applications", Wiley, 2016 Publication	1%
6	Submitted to President University Student Paper	1%
7	pdfs.semanticscholar.org Internet Source	1%
8	kesehatanlingkunganhesty.blogspot.com Internet Source	1%
9	Tanaka, S.. "Vapor infiltration techniques for spin-on mesoporous silica films", Thin Solid Films, 20060120 Publication	1%
10	aip.scitation.org Internet Source	1%

Exclude quotes Off

Exclude matches Off

Exclude bibliography Off